

9006 SFR X-Cure Spray

2K Ultra Rapid Clear Coat

silco[®]

Ultra fast drying clear coat for perfect refinish results within minutes.



- / Exceptionally fast drying at 60°C or 20°C
- / Only 7-9 min at 60°C
- / Immediate polish after cooling down
- / Perfect gloss retention & UV protection
- / Very easy application

9006 SFR X-Cure Spray

2K Ultra Rapid Clear Coat

Drying time

20°C	90 min
60°C	7-9 min

Flash-off	max 5 min
Potlife	6-8 h

*Indicative times subject to thinner type/application/wet film thickness/environment ...

*At normal ambient conditions (20-23°C, 40-50% RH)

Product info

Highly productive 2K rapid drying clear coat with perfect gloss. Very fast drying without spray booth baking allows fuel and electricity savings. Easy and quick application with good leveling and perfect finish.

How to use?

Hold the can as vertical as possible and ensure a distance of approx. 15-20 cm.

Two normal coats (with max 5 minutes flash-off) will result in 90 minute drying time.

For further and updated information please refer to the TDS published on www.silco.si.

Packaging

9006 SFR X-Cure Spray
2K Ultra Rapid Clear Coat

Prod. Nr.	Content
9006-0,4	400 ml

How to activate?

