

9050 X5 HS Clear Coat

HS High Gloss Clear Coat

Top quality clear for all kind of repairs.

silco[®]

- / Very easy application & excellent overflow
- / 4 Hardeners
- / Long lasting gloss retention & UV protection
- / Immediate polishing after cooling down

www.silco.si/en



9050 X5 HS Clear Coat

HS High Gloss Clear Coat

Mixing ratio 2:1

Hardener	Extra Fast 9220	Fast 9230	Standard 9250	Slow 9270
Drying time*				
20°C/68°F	~8 h	~10 h	~12 h	~14 h
60°C/140°F	~15 min	~20 min	~25 min	~30 min
IR	~10 min	~15 min	~15 min	~20 min
Flash-off 20°C/68°F	5–10 min			
Potlife 20°C/68°F	60–120 min			
Thinner	No thinner is needed.			

*Indicative times subject to hardener and thinner type/application/environment...

How to use?

Extra fast and fast hardeners are recommended for use on vertical surfaces. Extra fast hardener and fast hardeners are to be used when drying will be done at room temperature. Use two full coats application method with flash off between coats (5–10 min). Flash off time and drying time depends on the combination of the hardeners used.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

Versatile, acrylic HS clear coat for professional refinish repair. A wide range of hardeners allows all kinds of repairs, regardless of the complexity of the conditions and not at the expense of affecting superior gloss appearance. X5 Clear Coat is characterized by ease of application, perfect gloss retention and UV resistance. Polishing is possible immediately after cooling.

Packaging

9050 X5 HS Clear Coat
HS High Gloss Clear Coat

Prod. Nr.	Content
9050-1	1 L
9050-5	5 L

Hardener / 9220 - 9270 HS Hardener
HS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9220-0,2 / 9220-0,5 / 9220-0,7 / 9220-2,5	200 ml / 500 ml / 700 ml / 2.5 L	Extra Fast
9230-0,2 / 9230-0,5 / 9230-0,7 / 9230-2,5	200 ml / 500 ml / 700 ml / 2.5 L	Fast
9250-0,2 / 9250-0,5 / 9250-0,7 / 9250-2,5	200 ml / 500 ml / 700 ml / 2.5 L	Standard
9270-0,5 / 9270-2,5	500 ml / 2.5 L	Slow