

PROFILLER

Series 1314

High thickness, acryl urethane primer added with zinc phosphates



TECHNICAL FEATURES

2K polyacrylic primer with excellent adhesion to iron, galvanized steel, light alloys and some plastics such as ABS, PS, PVC and thermosetting plastics. The primer is the ideal substitute for epoxy primers in environmental conditions of application with temperatures below 12°C. Compared to common epoxy primers, in unfavorable conditions, the product grants fast polymerization and consequently allows rapid handling of the products.

APPLICATION FIELD

The product is ideal as primer for industrial, agricultural and earthmoving machinery, industrial bodywork, metal structures, machine tools.

GENERAL INFORMATION

System: Two pack - 2K

Nature: Solvent-based

Packages: 20 kg

Colors ready in stock: Grey Ral 7038, White

Suitable Substrates: Iron, Cast iron, Galvanized surfaces, Light alloys, Thermoplastics (ABS, PVC, PC), Fiberglass and Thermosetting plastics, Sandblasted Iron - Sandblasting Sa 1-2, Sandblasted Iron - Sandblasting Sa 2,5-3, Hot-dip galvanization

Overcoatable with: Epoxy, acrylic and polyurethane enamels

SUBSTRATE PREPARATION

The surface pre-treatment process, to be carried out prior to the application of the coating product, is of considerable importance in order to obtain and guarantee optimal and long-lasting results and performance over time. The substrate must be perfectly clean, dry, degreased and free from rust and/or calamine. It is also advisable to make sure that the substrate is free from particles and other paints that are not perfectly adherent or incompatible with the coating of paint that will be applied. For the purpose of a correct and complete preparation, it is recommended to consult, where necessary, the explanatory notes attached to the technical data sheet, the painting manual and the technical assistance service of the Research & Development Laboratory. The explanatory notes, specifically, depending on the type of surface and the result to be obtained, indicate different pre-treatment methods such as degreasing, manual and mechanical cleaning using special equipment, mechanical preparations (scraping, sanding, tapping, brushing), light or accurate sandblasting, shot blasting, shot peening and wet sandblasting (or hydro sandblasting). In case of particularly difficult surfaces, such as bright galvanized steel, stainless steel, thermosetting powders, pre-coted sheets, the preparation with mechanical preventive treatment such as mild sandblasting, sanding and/or brushing is necessary

APPLICATION

Application conditions

The application of the coating product is subject to various factors such as environmental conditions (among which it is necessary to mention temperature, humidity and ventilation), geometry and laboriousness of the products to be painted, surface profiles and thicknesses to be applied. The application system to be used is of particular importance as, depending on the type of system, various parameters may vary including the transfer efficiency of the coating product, the overspray, the aesthetic appearance obtained, the sagging stability of the product and the ease or complexity of application. For these reasons, prior to applications on systems and lines of considerable scope, it is advisable to contact the technical assistance service in order to carry out the inspection and the necessary surveys for a consultancy activity relating to the application methods and the definition of ad hoc technical details on the plant in question.

EQUIPMENT	VISCOSITY	NOOZLE	PRESSURE	NOTES
AIRBRUSH - CUP GUN	25" - 45" Ford Cup 4	1,7 - 1,9 mm	3,5 - 4 bar	-
AIRLESS	F&K technical assistance	F&K technical assistance	F&K technical assistance	F&K technical assistance
AIRMIX	Depending on application parameters	13 - 15	60 - 100 bar	-
ELECTROSTATIC	-	-	-	Contact technical assistance to decide the suitable antistatic additive

PROFILLER Series 1314

CATALYSIS

SERIES	HARDENER	CATALYSIS	USE	POT LIFE AT 20°C	PACKAGE
0929	PUR ALIPHATIC HARDENER	25% by weight (100 + 25)	Non yellowing for exterior use	4 hours	5 kg
1392	HS PLUS 420 HARDENER	12,5% by weight (100 + 12,5) or 4:1 by volume	HS, slow hardener suitable for outdoor applications	3 hours	2,5 l

ENVIRONMENTAL CONDITIONS



ENVIRONMENT
TEMPERATURE

5°C - 35°C



SUBSTRATE
TEMPERATURE

5°C - 35°C



RELATIVE
HUMIDITY

60 %



SHELF LIFE

Store 2 years in original sealed packaging at +5/+35°C.

TECHNICAL DATA



THEORETICAL AVERAGE SPREADING RATE	APPLICATION	DILUTION	GLOSS	WET FILM THICKNESS EACH COAT	DRY FILM THICKNESS EACH COAT	N° OF COATS	TOTAL DRY FILM THICKNESS	THEORETICAL AVERAGE CONSUMPTION
5,9 m²/kg each coat at the dry film thickness of 60 µ	Spray	10% with PUR Thinner Series 0988	15 - 25 gloss	128 µ	60 µ	1 or 2 coats to achieve the total desired thickness	90 µ	167 g/m²

DRYING



OVERCOATING INTERVAL	AIR DRYING	DUST-FREE DRYING	DRY TO TOUCH	DRY THROUGH	FULL CURE	FLASH OFF	STOVING DRYING	RESISTANCE TO TEMPERATURE
6 - 24 hours	20°C	20 - 30 minutes	1 - 2 hours	24 - 36 hours	7 days	15 - 20 minutes at 20°C	20 - 30 minutes at 60°C	80°C

WARNINGS AND RECOMMENDATIONS

- Being an anticorrosive primer, if exposed outdoors or where a long maintenance of the initial characteristics is required, it is necessary to apply a suitable protective final coat.
- The color match is evaluated after the application and drying of the product.
- Shelf Life Component B: the shelf life of the hardener used with Component A is 12 months.
- The product can be used to replace epoxy primers in non-optimal environmental conditions and in case of low temperatures (below 12°C).
- Plastic supports (ABS, PC, PVC) must be clean, dry, degreased and free from release agents.
- After 48-72 hours the film requires mechanical preparation (sanding or polishing).

PROFILLER

Series 1314

SUPPLY TECHNICAL DATA

Composition: Hydroxylated acrylic
Reference color: Gray Ral 7038
% solid content by weight: $70 \pm 2\%$
% solid content by volume: $51 \pm 2\%$
VOC: 429 ± 2 g/l
VOS: $30 \pm 2\%$

PARAMETER	DATA	TEST METHOD
GLOSS	15 - 25 gloss 60°	ISCOL 6
SPECIFIC WEIGHT	1,4 - 1,55 g/ml	ISCOL 2
VISCOSITY	6500 - 7500 mPa.s (20°C) Rod 4 Speed 20	ISCOL 1

MIXING RATIO A+B

Specific weight after catalysis (A+B): $1,3 \pm 0,05$ g/ml
% solid content by weight (A+B): $63 \pm 2\%$
% solid content by volume (A+B): $47 \pm 2\%$
VOC (A+B): 477 ± 2 g/l
VOS (A+B): $37 \pm 2\%$

METHOD	0929	1392
A+B BY WEIGHT	100 + 25	100 + 12,5
A+B BY VOLUME	100 + 35	4:1

NOTES

Cleaning tools: At the end of the application, carefully wash the spray guns, the painting systems and the containers with a suitable thinner and store the tools dry to avoid encrustations.

Sanitary labelling: Handle the product with care. Make reference to the MSDS and respect the national and local regulations in force concerning personal and environmental safety.

Additional notes:

- The data reported in this data sheet have been obtained using only Franchi&Kim production materials (coatings, hardeners, thinners) applied in accordance with the specifications described. The improper use of thinners and/or hardeners, different from those suggested or not manufactured by Franchi & Kim, can compromise application features, performances and final curing of the product. Therefore, in case of mixed coating systems with Franchi & Kim and other brand products, the conformity of the results with the parameters indicated in the technical data sheet cannot be granted.
- The times related to pot life and drying intervals refer to a standard temperature of 20°C, except when it is expressly indicated.
- The gloss indicated and tested may change during the application phase because it can be influenced by the following factors: realized color, thickness, number of coats, environmental conditions, thinner and hardener used if different from those listed in the technical data sheet.
- The data relating to section mixing ratio A+B are to be considered referring only to the first recommended catalyst.
- The spreading rates are theoretical, indicative and intended per coat as they can be influenced by the color and the application system. Practical application test is suggested.
- Pot Life times have been defined at the temperature of 20°C, therefore higher or lower temperatures, hardeners, environmental conditions and humidity different from the standard can influence in defect or in excess the duration of the Pot Life.

The information contained in this technical document is correct and accurate to the best of our knowledge, and should therefore be considered reliable. In any case, they cannot imply a guarantee on our part, as certain factors such as the preparation of the product and the substrate, the conditions of use, application, drying and overcoating, as well as the state of conservation of the products, are outside our strict control. It is responsibility of the user to verify the suitability of the products for the specific use, as well as the correct and precise execution of the work in accordance with the content of the technical data sheet, the recommended coating system and preparation of the support. For further information regarding the method of application and conditions of use, it is recommended to contact our technical support service. It should be noted that the packaging image could have a placeholder purpose and could therefore be an indicative reference. The packages indicated may vary according to the additions or changes of the annual price lists. This document replaces all previous versions. In any case, it is advisable to refer to the annexes with the explanatory notes to better understand and deepen the parameters of the technical data sheet. The updated edition, available on the website www.franchi-kim.com in the section technical data sheets of the download area is to be considered the only ones to consult as reference.

ESTALIA Performance Coatings Spa

Via Giacomo Matteotti, 160 - 25014 Castenedolo - Brescia - Italia - Tel. +39 030 21 35 55 - Fax +39 030 27 31 664 - www.franchi-kim.com - www.estaliacoatings.com