

ACRYVER GLOSSY DTM HS

Series 1788

DTM, glossy, acryl-polyurethane enamel for metal, light alloys and galvanized steel



TECHNICAL FEATURES

DTM anticorrosive glossy acrylic polyurethane enamel suitable for direct applications on iron and galvanized sheet with high adhesion properties. Glossy product that can be used on various surfaces such as plastics and thermosetting materials, metals and glass (after adding the adhesion promoter additive). The product has good resistance to water and chemicals in general, and also has good scratch resistance.

APPLICATION FIELD

Glossy acrylic polyurethane enamel direct to metal indicated as a finishing primer for metal supports, with good anticorrosive properties. Product ideal for applications of parts and components of the Ace sector, robotics and industrial automation, giving high productivity and speed of handling.

GENERAL INFORMATION

System: Two pack - 2K

Nature: Solvent-based

Packages: 3,3 kg - 17 kg

Tinting Service: Tinting service with solvent-based colorants Series 0615

Suitable Substrates: Iron, Galvanized surfaces, Light alloys, Thermoplastics (ABS, PVC, PC), Fiberglass and Thermosetting plastics, Sandblasted Iron - Sandblasting Sa 1-2, Sandblasted Iron - Sandblasting Sa 2,5-3, Hot-dip galvanization

Color fans and color cards: Ral 841 GL, Ral Design, Ncs 1950, ColoradoMix 1040, Colorado Box 2.0

SUBSTRATE PREPARATION

The surface pre-treatment process, to be carried out prior to the application of the coating product, is of considerable importance in order to obtain and guarantee optimal and long-lasting results and performance over time. The substrate must be perfectly clean, dry, degreased and free from rust and/or calamine. It is also advisable to make sure that the substrate is free from particles and other paints that are not perfectly adherent or incompatible with the coating of paint that will be applied. For the purpose of a correct and complete preparation, it is recommended to consult, where necessary, the explanatory notes attached to the technical data sheet, the painting manual and the technical assistance service of the Research & Development Laboratory. The explanatory notes, specifically, depending on the type of surface and the result to be obtained, indicate different pre-treatment methods such as degreasing, manual and mechanical cleaning using special equipment, mechanical preparations (scraping, sanding, tapping, brushing), light or accurate sandblasting, shot blasting, shot peening and wet sandblasting (or hydro sandblasting).

In the presence of critical substrates such as stainless steel or galvanized sheet, surface preparation is required by mechanical action such as sandblasting, sanding or phosphodegreasing.

APPLICATION

Application conditions

The application of the coating product is subject to various factors such as environmental conditions (among which it is necessary to mention temperature, humidity and ventilation), geometry and laboriousness of the products to be painted, surface profiles and thicknesses to be applied. The application system to be used is of particular importance as, depending on the type of system, various parameters may vary including the transfer efficiency of the coating product, the overspray, the aesthetic appearance obtained, the sagging stability of the product and the ease or complexity of application. For these reasons, prior to applications on systems and lines of considerable scope, it is advisable to contact the technical assistance service in order to carry out the inspection and the necessary surveys for a consultancy activity relating to the application methods and the definition of ad hoc technical details on the plant in question.

EQUIPMENT	VISCOSITY	NOOZLE	PRESSURE	NOTES
AIRBRUSH - CUP GUN	25" - 45" Ford Cup 4	1,4 - 1,7 mm	3,5 - 4 bar	-
AIRMIX	Depending on application parameters	11 - 13	60 - 100 bar	-
ELECTROSTATIC	-	-	-	Contact technical assistance to decide the suitable antistatic additive

ACRYVER GLOSSY DTM HS Series 1788

CATALYSIS

SERIES	HARDENER	CATALYSIS	USE	POT LIFE AT 20°C	PACKAGE
0929	PUR ALIPHATIC HARDENER	30% by weight (100 + 30)	Non yellowing for outdoor use	4 hours	1 l - 5 kg
1383	STANDARD HS HARDENER	30% by weight (100 + 30)	Slow, non yellowing for outdoor use	4 hours	1 l - 5 kg
1392	HS PLUS 420 HARDENER	15% by weight (100 + 15) or 4:1 by volume	HS, slow for exterior use	4 hours	1 l - 2,5 l

ENVIRONMENTAL CONDITIONS



ENVIRONMENT
TEMPERATURE

5°C - 35°C



SUBSTRATE
TEMPERATURE

5°C - 35°C



RELATIVE
HUMIDITY

60 %



SHELF LIFE

Store 2 years in original sealed packaging
at +5/+35°C.

TECHNICAL DATA



THEORETICAL AVERAGE SPREADING RATE	APPLICATION	DILUTION	GLOSS	WET FILM THICKNESS EACH COAT	DRY FILM THICKNESS EACH COAT	N° OF COATS	TOTAL DRY FILM THICKNESS	THEORETICAL AVERAGE CONSUMPTION
6,6 m ² /kg each coat at the dry film thickness of 60 µ	Spray	5-7% with PUR Thinner Series 0988	88 - 98 gloss	131 µ	60 µ	1 or 2 coats to achieve the total desired thickness	100 µ	151 g/m ²

DRYING



OVERCOATING INTERVAL	AIR DRYING	DUST-FREE DRYING	DRY TO TOUCH	DRY THROUGH	FULL CURE	FLASH OFF	STOVING DRYING	RESISTANCE TO TEMPERATURE
4 - 96 hours (after it is necessary to sand)	20°C	10 - 15 minutes	30 - 40 minutes	1 - 2 days	14 days	5 - 10 minutes at 20°C	30 minutes at 50°C - 60°C	80°C short temperature leap at 100°C - 120°C

ACRYVER GLOSSY DTM HS Series 1788

WARNINGS AND RECOMMENDATIONS

- Being a direct to metal product, it does not require the application of a suitable primer.
- The use of nitro thinners for the application of polyurethane coating systems can create pitting phenomena on the surface of the dried film. Furthermore, the presence of partially reactive solvents can give rise to undesired reactions, reducing the aesthetic and mechanical features of the system. The choice of unsuitable regenerated thinners can create problems of color change, product sedimentation and less effectiveness in reducing viscosity.
- The product is limitedly resistant to solvents generally intended as temporary contact and limited in time.
- The product can be applied directly, without the aid of a primer, only in the presence of not extremely shiny and new galvanized steel.
- The color match is evaluated after the application and drying of the product. It is recommended to carry out practical tests, such as spreading or applying the colored product on small surfaces made of suitable material, before proceeding with the product painting.
- After having colored the product with the suitable colorants, mix it in a short time.
- In order not to incur financial penalties, after having colored a product with tinting machine, send the MSDS and apply the appropriate legal labelling printable using the Databook P&C tinting software.
- For DTM, one coat, low opacity colored products (yellow, orange, red), to check the shade, apply two coats of 100 μ w.f.t. of the product.
- Shelf Life Component B: the shelf life of the hardener used with Component A is 12 months.

SUPPLY TECHNICAL DATA

Composition: Modified acrylic

Reference color: White

% solid content by weight: $64 \pm 2\%$

% solid content by volume: $50 \pm 2\%$

VOC: 446 ± 2 g/l

VOS: $36,7 \pm 2\%$

PARAMETER	DATA	TEST METHOD
VISCOSITY	900 - 1000 mPa.s (20°C) Rod 2 Speed 20	ISCOL 1
SPECIFIC WEIGHT	1,15 - 1,25 g/ml	ISCOL 2
GLOSS	88 - 98 gloss 60°	ISCOL 6

MIXING RATIO A+B

Specific weight after catalysis (A+B): $1,22 \pm 0,05$ g/ml

% solid content by weight (A+B): $57 \pm 2\%$

% solid content by volume (A+B): $45 \pm 2\%$

VOC (A+B): 490 ± 2 g/l

VOS (A+B): $42,8 \pm 2\%$

METHOD	0929	1383	1392
A+B BY WEIGHT	100 + 30	100 + 30	100 + 15
A+B BY VOLUME	100 + 40	100 + 40	4:1

TINTING SERVICE

BASE	BASE PACKAGING	COLORED PACKAGING	% MIXING RATIO
BINDER	2,47 kg 12,75 kg	3,3 kg 20 kg	75 - 25
WHITE BASE	16,15 kg	20 kg	95 - 5

ACRYVER GLOSSY DTM HS Series 1788

NOTES

Cleaning tools: At the end of the application, carefully wash the spray guns, the painting systems and the containers with a suitable thinner and store the tools dry to avoid encrustations.

Sanitary labelling: Handle the product with care. Make reference to the MSDS and respect the national and local regulations in force concerning personal and environmental safety.

Additional notes:

- The data reported in this data sheet have been obtained using only Franchi&Kim production materials (coatings, hardeners, thinners) applied in accordance with the specifications described. The improper use of thinners and/or hardeners, different from those suggested or not manufactured by Franchi & Kim, can compromise application features, performances and final curing of the product. Therefore, in case of mixed coating systems with Franchi & Kim and other brand products, the conformity of the results with the parameters indicated in the technical data sheet cannot be granted.
- The data relating to section mixing ratio A+B are to be considered referring only to the first recommended catalyst.
- The spreading rates are theoretical, indicative and intended per coat as they can be influenced by the color and the application system. Practical application test is suggested.
- Pot Life times have been defined at the temperature of 20°C, therefore higher or lower temperatures, hardeners, environmental conditions and humidity different from the standard can influence in defect or in excess the duration of the Pot Life.

The information contained in this technical document is correct and accurate to the best of our knowledge, and should therefore be considered reliable. In any case, they cannot imply a guarantee on our part, as certain factors such as the preparation of the product and the substrate, the conditions of use, application, drying and overcoating, as well as the state of conservation of the products, are outside our strict control. It is responsibility of the user to verify the suitability of the products for the specific use, as well as the correct and precise execution of the work in accordance with the content of the technical data sheet, the recommended coating system and preparation of the support. For further information regarding the method of application and conditions of use, it is recommended to contact our technical support service. It should be noted that the packaging image could have a placeholder purpose and could therefore be an indicative reference. The packages indicated may vary according to the additions or changes of the annual price lists. This document replaces all previous versions. In any case, it is advisable to refer to the annexes with the explanatory notes to better understand and deepen the parameters of the technical data sheet. The updated edition, available on the website www.franchi-kim.com in the section technical data sheets of the download area is to be considered the only ones to consult as reference.

ESTALIA Performance Coatings Spa

Via Giacomo Matteotti, 160 - 25014 Castenedolo - Brescia - Italia - Tel. +39 030 21 35 55 - Fax +39 030 27 31 664 - www.franchi-kim.com - www.estaliacoatings.com