

6110 B11 SFR Superfast


Super fast and easy to sand semilightweight polyester putty. The putty is sandable in 8 minutes (20°C) without paper clogging. Sanding is easy and fast.

- specific weight 1.3-1.35 kg/L
- ready to sand in 8 - 10 minutes from application
- excellent adhesion to various substrates
- very easy to spread
- non-porous, smooth surface
- can be used as filling and fine putty
- excellent sanding, beginning with P150

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. For aluminium and galvanized steel, use matting pad and matting paste to improve adhesion.

Mixing ratio



By weight

| | |
|--|---------------------------|
| 6110 B11 SFR Superfast | 100 % |
| 6065/6067 Hardener for Polyester putty | 2 - 3 % (do not overdose) |

Mix the putty and hardener thoroughly until the colour is even.

Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat.

Application



Recommended minimum application temperature is 10°C.

Drying

6110 B11 SFR Superfast



Ready to sand [20 °C/68 °F]: 8 - 10 min

Pot life [20 °C/68 °F]: 3 - 4 min

It is not recommended to use IR or any other high temperature drying equipment if the temperature control is not possible, while the maximum temperature for drying of the putty is 45°C/113°F.

Forced drying of polyester putty at elevated temperatures can lead to problems with adhesion.

Sanding

Only dry sanding

P150 - 240

Complementary products

6065 Putty hardener, standard (red cap)

6065-CT-0,06 Putty hardener (in combination with 1,65 L putty cartridge)

6067 Putty hardener, slow (blue cap)*

* Not all blue BPU hardeners on the market are slow!

Packaging

| Product no. | Description | Volume/Weight | Packaging [pcs/box] |
|--------------------|--------------------|----------------------|----------------------------|
| 6110-1 | White | 1L | 6 |
| 6110-CT-1,65 | White | 1,65 L | 4 |
| 6110-3 | White | 3 L | 2 |

Polyester putty hardener 6065 is included.

Volatile organic compounds

The VOC value for this product is 245 g/L.

The product category is VOC 2004/42/IIIB (b) (250)

Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.



Technical data sheet

2024-8

6110 B11 SFR Superfast

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.