

6060 B6 Multisoft


Universal high-performance polyester putty, characterized by its fine texture, ease of application and good sanding.

- Excellent adhesion to galvanized and electro-zinc-coated metals, steel surfaces and aluminium
- Very easy to spread
- Non-porous, smooth surface
- Excellent sanding
- Specific weight: 1.94 kg/L

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. For aluminium and galvanized steel, use matting pad and matting paste to improve adhesion.

Mixing ratio

 +	By weight	
	6060 B6 Multisoft	100 %
	6065/6067 Hardener	2 - 3 % (do not overdose)

Mix the putty and hardener thoroughly until the colour is even.

Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat.

Application



Recommended minimum application temperature is 10°C.

Drying

6060 B6 Multisoft



Ready to sand 20 - 30 min
[20°C/68°F]

Pot life 3 - 4 min
[20°C/68°F]

It is not recommended to use IR or any other high temperature drying equipment if the temperature control is not possible, while the maximum temperature for drying of the putty is 45°C/113°F.

Sanding



Only dry sanding!
P120 - P240

Packaging

Product no.	Description	Volume/Weight	Packaging [pcs/box]
6060-0,45	Beige	450 g	12
6060-1,9	Beige	1,9 kg	6

Polyester putty hardener 6065 is included.

Complementary products

6065 Putty hardener, standard (red cap)

6067 Putty hardener, slow (blue cap)*

* Not all blue BPU hardeners on the market are slow!

Volatile organic compounds

The VOC value for this product is 52 g/L.

The product category is VOC 2004/42/IIIB (b)(250)

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.



Technical data sheet

2024-20

6060 B6 Multisoft

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.