

4020 Z-Prime


Quick-drying protection against corrosion with excellent long-term effects. Contains 99% pure zinc.

- primer for all metal parts in which corrosion protection is required
- repaintable without extra primer
- good electrical conductivity, therefore also suitable as welding marking color
- quick-drying
- provides a smooth, non-porous layer of lacquer
- resistant to salt water
- wet-on-wet application

Substrate preparation


The surface must be dry and free from oil, grease, dust, adhesions, and rust. For optimal substrate pretreatment, sandblasting is recommended.

Mixing ratio



The product is ready for use!

Spraygun setup



Shake it for about 2 minutes after the intensive audible rattling of the mixing balls

Optimal application temperature:	20 °C
----------------------------------	-------

Number of coats:	2
------------------	---

Spraying distance:	20 - 25 cm
--------------------	------------

Flash-off between layers:	Apply second layer when the first layer is totally dry.
---------------------------	---

Dry film thickness:	60 - 80 µm
---------------------	------------

After spraying turn the can upside down and spray until the valve is clean. It is strongly recommended that ready to use product is applied at temperature above 15 °C/59 °F.

Packaging



Technical data sheet

2025-1

4020 Z-Prime

Product number	Description	Volume/Weight	Packaging
4020-0,5	Grey	500 mL	12

Volatile organic compounds

The VOC value for this product is 629 g/L

Shelf life

Min. 24 months from the production date under normal storage conditions and unopened can, at a storage temperature of -5 °C to +30 °C.

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.