

silco®

- / Fast drying
 - 15 minutes at 60°C
 - 3-4 hours at 20°C
- / Immediate polishing after cooling down
- / Superior gloss retention & UV protection
- / Very easy application & leveling



9110 X11 Spectrum Lite

UHS 420 rapid clear coat

Product info

Fast drying UHS clear coat characterized by its short drying time, high gloss, long-lasting gloss retention and perfect levelling.

Mixing ratio 2:1

Hardener	9122 / 9123 / 9125 / 9127 UHS Hardener Extra Fast / Fast / Standard / Slow
Drying time*	
20°C/68°F	3-4 h
40°C/104°F	25-30 min
60°C/140°F	15 min
Flash-off 20°C/68°F	5-10 min
Potlife 20°C/68°F	60 min
Thinner	5-10 % (7050 Standard, 7070 Slow)

*Indicative times subject to hardener and thinner type/application/environment...

Packaging

9110 X11 Spectrum Lite
UHS 420 rapid clear coat

Prod. Nr.	Content
9110-1	1 L
9110-5	5 L

Hardener / 9122 - 9127 UHS Hardener
UHS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9122-2,5	2.5 L	Extra Fast
9123-0,5 / 9123-2,5	500 ml / 2.5 L	Fast
9125-0,33 / 9125-0,5 / 9125-1 / 9125-2,5	330 ml / 500 ml / 1 L / 2.5 L	Standard
9127-1 / 9127-2,5	1 L / 2.5 L	Slow