

9060 X6 UHS Clear Coat

The versatile high-quality acrylic UHS varnish is characterized by ease of use and excellent gloss of the painted surface.

- easy application, good leveling, good gloss
- drying: 20 - 30 min (60°C)
- polishing is possible immediately after cooling
- excellent gloss resistance and UV protection
- VOC compliant (<420 g/L)

Preparation of the base

The base coat must be completely dry. Clear coat has been tested on WB and SB basecoats.

Substrate preparation

<div>2 : 1</div>		By volume	By weight
	9060 X6 UHS Clear Coat	2	See table on bottom
	9122/9123/9125/9127 2K Hardener	1	
	7030/7050 Acrylic Thinner	0 % *	
* 5% of thinner can be added if necessary. In this case, the product no longer complies with the VOC Directive.			

Application



Number of layers:	1,5 - 2	
Flash-off between layers [20°C]	5 - 10 min	
Dry film thickness:	50 - 60 µm	

Extra fast and fast hardeners are recommended for use on vertical surfaces and spot repairs. Light half coat followed by full closed coat without flash off can be used for spot and quick repairs.

For all other repairs, use two full coats application method, with flash off between coats (5-10 min). Flash off time and drying time depends on the combination of the hardeners and thinners used.

9060 X6 UHS Clear Coat

Drying



Dry to polish (60°C)	20 - 30 min
Dry to polish (20°C)	8 - 14 h
IR shortwave	10 - 15 min
Potlife (20°C)	30 - 45 min

Complementary products

9122 (ultra fast), 9123 (fast), 9125 (standard), 9127 (slow) 2K Hardener

Testing of material

Any kind of testing of the applied material (adhesion test, stone-chip test, chemical resistance, salt chamber test ...) has to be done at least 15 days after the application.

Packaging

Product no.	Description	Volume/Weight	Packaging [pcs/box]
9060-1	/	1 L	6
9060-5	/	5 L	3

Volatile organic compounds

The VOC value for this product is 420 g/L

The product category is VOC 2004/42/II B(d)(420).

Shelf life

Min. 24 months from the production date under normal storage conditions and unopened can.

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any



Technical data sheet

2024-6

9060 X6 UHS Clear Coat

purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.

Mixing ratio by weight

Volume of RFU paint required	CLEARCOAT	CLEARCOAT + HARDENER
(ml)	(g)	(g)
100	68	102
250	170	256
330	224	338
500	340	512
750	510	768
1000	680	1023