

## **9009 Rim Restore**


**Glossy silver wheel paint for restoring the appearance of wheel rims and decorative wheel covers.  
Based on nitrocellulose resin with high quality aluminium pigments.**

- very good adhesion to a variety of substrates
- suitable for chrome, metal and plastic parts
- quick drying
- high covering power, economical in use

### **Substrate preparation**

Surfaces must be clean, dry and degreased.

### **Mixing ratio**



By volume

9009 Rim Restore	1
7050 Acrylic Thinner	0,4-0,5 (40 - 50% vol.)


Shake and mix well before use!

### **Application**



Number of layers:	1,5 - 2
Dry-film thickness [µm]:	20 - 30

### **Flash-off [20 °C/68 °F]**



Between coats [20 °C]:	0 - 5 min
---------------------------	-----------

### **Spray gun setup**

## **9009 Rim Restore**



Nozzle:	1,2 - 1,4 mm
Pressure (upper cup):	1,6 - 1,8 bar
Pressure (suction cup)	Verify manufacturers' info

### **Drying**



Dust dry [20 °C]:	10 - 15 min
Dry to assemble [20 °C]:	120 - 180 min
Completely dry [20 °C]:	24 h

### **Complementary products**

#### **Thinners**

7050 Acrylic Thinner, Standard

### **Testing of material**

Any kind of testing of the applied material (adhesion test, stone-chip test, chemical resistance, salt chamber test ...) has to be done at least 15 days after the application.

### **Packaging**

Product no.	Description	Volume/Weight	Packaging [pcs/box]
9009-0,75	Silver	750 ml	6

### **Volatile organic compounds**

The VOC value for this product is 735 g/L

The product category is VOC 2004/42/II B(e) (840).

### **Shelf life**

Min. 24 months from the production date under normal storage conditions and unopened can.



Technical data sheet

2025-1

## 9009 Rim Restore

### Additional information

---

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

**IMPORTANT:** This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.