

2015 Underbody Bitumen

Underbody bitumen based coating, developed for dip and sag free application that ensures excellent and durable protection against corrosion, stone chip, salt, etc. Can be applied on parts of chassis, under floor panel, inside wheel casting, etc. Avoid application on brake or exhaust system.

- Excellent barrier formation
- Easy to apply
- Strong adhesion on raw or painted metal, plastic materials or old underbody protection
- Builds protective film against stone chips, salt, noise etc.
- Resistant to water, acid, alkaline
- Not over-paintable

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free.

Mixing ratio

The product is ready to use!
Shake the product before use.

Spray gun set /air inlet

Pressure: 2 - 5 bar

Application

Number of coats	1 - 2	
Total dry film build [microns]	300	
Application air temperature	5 - 25°C (41 - 77°F)	

Drying

Dust dry [20°C/68°F]	3 - 5 h	
Touch dry [20°C/68°F]	12 - 16 h	

2015 Underbody Bitumen

Complementary products

Application gun (Prod. Nr. 2006)

Packaging

Product no.	Description	Volume/Weight	Packaging [pcs/box]
2015-1	Black	1 kg	12

Volatile organic compounds

VOC value for this product is 500 g/L.

VOC category of this product is 2004/42/II B(e) (840).

Shelf life

Min. 24 months from the production date under normal storage conditions and unopened can.

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.